

Kane Ace® MX 120

25% Core Shell Rubber in unmodified, liquid epoxy resin based on Bisphenol-A

Description:

Kane Ace® MX 120 is a 25% concentrate of core shell rubber (CSR) toughening agent in unmodified liquid epoxy resin based on Bisphenol-A. MX 120 is stable and the CSR remains completely dispersed under normal handling, formulating and curing conditions. The concentrate can be mixed or diluted with a variety of epoxy resins and diluents.

The resulting composite, adhesive or coating exhibits improved fracture toughness, lap shear strength, and durability without sacrificing glass transition temperature or other thermal properties related to the cross-link density. The MX 120 product is also free of ionic and organic contaminants.

Applications:

Kane Ace® MX 120 is suitable for use in the production of composites from prepregs, filament winding, pultrusion, and resin transfer molding. Other applications include

coatings, adhesives, copper-clad laminates and electrical castings. Please see your Kaneka representative for more detailed information on applications.

Curing Agents:

Kane Ace® MX 120 is compatible with typical cold, warm and hot curing agents for coatings, adhesives and composites.

Storage Conditions:

Kane Ace® MX 120 is suitable for use for at least 12 months from the date of manufacture when stored in the original, unopened container. The product should be kept away from excessive hot or cold to prevent crystallization of the epoxy.

Handling Precautions:

Safe practices and procedures as outlined in the applicable MSDS must be followed.

Characteristics (Preliminary Data):

| | |
|---------------------------------|------------------------------------|
| Appearance: | Uniform, blue/yellow clear liquid. |
| CSR Content: | 25 +/- 1 wt% |
| Epoxy Equivalent Weight: | 243 +/- 11 g/eq. |
| Viscosity @ 50°C: | 22,000 +/- TBD cPs |
| Flash point: | >220 °C |
| Density : | 1.1 |

Kaneka Texas Corporation's (the Seller) policy is one of continuous development and improvement and in line with that policy we reserve the right to implement improvements and alterations to our products from time to time without giving prior written notice to customers. While all information contained in this publication is considered accurate to the best of the knowledge of the Seller, all specifications, capacities, weights, measurements and other data and particulars relating to the Seller's goods set out in this brochure are approximate only. Performance figures are included only as an indication of past performance and do not constitute a condition, warranty or guaranteed a future performance. Customers must ensure and satisfy themselves that the products to be purchased will be fit for the particular purpose for which they intend to use them and in so far as materials not manufactured or supplied by the Seller are used in conjunction with, or instead of the Seller's products, it is the responsibility of the customer to obtain all technical data and information relating to such materials and to satisfy themselves that those products are suitable for use with the Seller's products and are fit for the purpose for which they propose to put them. No liability can be accepted in respect of the use of the Seller's products in conjunction with other materials. Employees, sub-contractors and agents of the Seller are not authorized to make any representations concerning the Seller's products and any advice and recommendation given by them to a customer as to the storage, application or use of the Seller's goods which is not confirmed in writing by a duly authorized officer of the Seller is followed or acted upon entirely at the customer's own risk, and the Seller shall not be liable for any such advice or recommendations if not so confirmed. The Seller does not accept any liability whatsoever arising out of the use of the information or the use, application, adaptation or processing of the products described herein. **Note:** This brochure annuls and replaces all publications issued hitherto.