

KANEKA TEXAS CORPORATION

KANEVINYL XEL-D SPECIFICATION

- VOLATILE MATTER % <= 0.3
- APPARENT SPECIFIC GRAVITY g/cc >=0.40
- K-VALUE(DIN) OF SOLUBLE PART TO THF(solvent) 57-61
- GEL FRACTION % 15-21

Revise : FEB., 98